



SUPCOAT BT 7011 MPC

Description

Standard peelable lidding film. SUPCOAT BT 7011 MPC is a transparent biaxially oriented polyester (BOPET) film with peelable seal property. Other side is chemically treated.

Properties

- · Peelable seal to APET, CPET
- · Superior mechanical strength
- · Excellent stiffness
- · Excellent machinability and flatness
- Good dimensional stability
- · Excellent chemical resistance
- · Easy open peelable seals
- Suitable for microwave applications & conventional oven

Applications

It is specially designed for use in lidding applications where peelable seal property is needed to wide range of substrates like APET, CPET. It does not seal to polyolefins such as PP and PE.

Chemical treatment is acrylate based which gives good adhesion to solvent based inks. Chemical treated side may be used as printing and lamination surface, but should be approved with present ink and lamination adhesive system used including aging.

Please contact customer service representetive for the application compliance.





Technical Features

	PROPERTIES	TEST METHOD	UNITS		BT 7011 MPC				
	HICKNESS	ASTM F2251	micron		17	21	25	38	
ı			Gauge		68	84	100	152	
ı,	'IELD	ASTM D4321	m²/kg		43,5	35,0	29,2	19,1	
			in²/Lbs		30.600	24.500	20.500	13.400	
•	JNIT WEIGHT	ASTM D4321	g/m²		23	28,6	34,2	52,4	
	HAZE	ASTM D1003		%	9				
	GLOSS (45°)	ASTM D2457		%		1	00		
	OXYGEN FRANSMISSION RATE 23°C-0%RH)	ASTM D3985	cc/m²/24hrs		≤ 100				
			cc/100in²/24hrs		≤ 6,5				
•	WATER VAPOUR FRANSMISSION RATE 38°C-90%RH)	ASTM F1249	g/m²/24hrs		≤ 30				
			g/100in²/24hrs		≤2				
	TENSILE STRENGTH AT BREAK	ASTM D882	N/mm²		240				
_			MD	Ib/in²	34.800				
			TD	N/mm²	260				
				lb/in²		37	.700		
	ELONGATION AT BREAK	ASTM D882	MD	%	140				
			TD		110				
	HERMAL SHRINKAGE 150 °C, 30 min, air)	ASTM D1204	MD TD	%	2,0 0,5				
				d Side/Metal	0,45				
	COEFFICIENT OF FRICTION	ASTM D1894	Other Side/Metal		0,40				
N	SURFACE ENSION	ASTM D2578	Dyne/	Chemical Side			38		
ľ			cm	Other Side			-		
	HEATSEAL RANGE	ASTM F88	°C		100-240				
			°F		212-464				
	HEATSEAL STRENGTH to APET/CPET 150°C, 4 MPa, 1 s) duct Identification (I	Internal	N/15mm		3,5				

Product Identification (Decision 97/129/EC): PET1

Regulatory Status

Our product complies with the applicable EC legislation on packaging involving direct contact with foods except metallized films. Full details are given on the Regulatory Compliance Certificate and can be found on our web site.

The information contained in this data sheet is true and accurate according to current state of our knowledge and intented to give general information on our products and their applications. Above values are to be considered as guidelines and not as product specifications. Since the actual conditions of use are beyond our control, users are advised to make their own tests at their specific conditions of laboratory and/or actual use. We suggest our customers to determine final suitability for their specific end uses.

Also be advised that information on this data sheet shall not be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing, pending or future patents.

The film shelf life is 6 months. Modified PU based ink series offer good adhesion and printability.

For related spec sheet with tolerance values, please contact our sales departments

STANDARD ROLL DIMENSIONS							
CORE INNER DIAMETER (ID)	CORE OUTER DIAMETER (OD)	LENGTH TOLERANCE	WIDTH TOLERANCE				
76 mm (3 in) & 152 mm (6 in)	530 mm & 790 mm	± % 10 for all OD's	- 0 & + 4 mm				



REV: 05 Date: 10.08.2022