



## SUPCOAT

### BT 7011 M1C

#### Description

Low haze peelable antifog lidding film. SUPCOAT BT 7011 M1C is a transparent, peelable BOPET film with smooth peel and excellent antifog property. Other side is chemically treated.

It has antifogging (antimist) property on peelable surface for fresh fruits and vegetable packaging where high visibility in cold environment is needed. The film retains its transparency by spreading the condensed water droplets into a continuous and uniform water layer and the packed foods stays clearly visible. It also protects the packed food against deterioration caused by droplets of water.

#### Properties

- Peelable seal to mono APET
- Superior haze and clarity
- Excellent mechanical strength and stiffness
- Excellent machinability and flatness
- Good dimensional stability
- Excellent chemical resistance
- Smooth and easy open peelable seals
- Excellent antifogging (antimist) property
- Suitable for microwave & conventional oven.
- Over printing varnish is strongly recommended when printing
- The film shelf life is 6 months

#### Applications

It is specially designed for use in lidding applications where it gives peelable seals to wide range of substrates like mono APET. But does not seal to polyolefins such as PP and PE. Chemical treatment is acrylate based which gives good adhesion to solvent based inks. Chemical treated side may be used as printing and lamination surface, but should be approved with present ink and lamination adhesive system used including aging. It is not suitable for metallization applications.

SUPCOAT BT 7011 M1C is not suitable for wet filling applications, with lots of water, fluid and oil contamination on trays.



## Technical Features

PROPERTIES	TEST METHOD	UNITS					BT 7011 M1C	
THICKNESS	ASTM F2251	micron	17	21	25	38		
		Gauge	68	84	100	152		
YIELD	ASTM D4321	m²/kg	43,5	35,0	29,2	19,1		
		in²/Lbs	30.600	24.500	20.500	13.400		
UNIT WEIGHT	ASTM D4321	g/m²	23,0	28,6	34,2	52,4		
HAZE	ASTM D1003	%	8					
GLOSS (45 °)	ASTM D2457	%	100					
OXYGEN TRANSMISSION RATE (23°C-0%RH)	ASTM D3985	cc/m²/24hrs	≤ 100					
		cc/100in²/24hrs	≤ 6,5					
WATER VAPOUR TRANSMISSION RATE (38°C-90%RH)	ASTM F1249	g/m²/24hrs	≤ 30					
		g/100in²/24hrs	≤ 2					
TENSILE STRENGTH AT BREAK	ASTM D882	MD	N/mm²	240				
			lb/in²	34.800				
		TD	N/mm²	260				
			lb/in²	37.700				
ELONGATION AT BREAK	ASTM D882	MD	%	140				
		TD		110				
THERMAL SHRINKAGE (150 °C, 30 min, air)	ASTM D1204	MD	%	2,0				
		TD		0,5				
COEFFICIENT OF FRICTION	ASTM D1894	Coated Side/Metal		0,25				
		Other Side/Metal		0,40				
SURFACE TENSION	ASTM D2578	Dyne /cm	Chemical Side	38				
			Other Side	-				
HEATSEAL RANGE	ASTM F88	°C		90-240				
		°F		194-464				
HEATSEAL STRENGTH to mono APET (150 °C, 4 MPa, 1 s)	Internal	N/15mm	RPET	NS				
			APET	3,5				

Product Identification (Decision 97/129/EC): PET1

Please be informed that additives used in antifog films are very sensitive to excess heat. Films should be kept in cool & dry places to maximize shelf life regarding antifog performance. We would also like to remind that antifog films should be used in 6 months after production.

### Regulatory Status

Our product complies with the applicable EC legislation on packaging involving direct contact with foods except metallized films. Full details are given on the Regulatory Compliance Certificate and can be found on our web site. The information contained in this data sheet is true and accurate according to current state of our knowledge and intended to give general information on our products and their applications. Above values are to be considered as guidelines and not as product specifications. Since the actual conditions of use are beyond our control, users are advised to make their own tests at their specific conditions of laboratory and/or actual use. We suggest our customers to determine final suitability for their specific end uses.

Also be advised that information on this data sheet shall not be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing, pending or future patents. The film shelf life is 6 months. Modified PU based ink series offer good adhesion and printability.

For related spec sheet with tolerance values, please contact our sales departments

STANDARD ROLL DIMENSIONS			
CORE INNER DIAMETER (ID)	CORE OUTER DIAMETER (OD)	LENGTH TOLERANCE	WIDTH TOLERANCE
76 mm (3 in) & 152 mm (6 in)	530 mm & 790 mm	± % 10 for all OD's	- 0 & + 4 mm