



SUPCOAT

BT 7011 HWX

Description

SUPCOAT BT 7011 HWX is a transparent biaxially oriented polyester (BOPET) film with peelable seal property. Other side is treated.

It has high resistant to water. Specially designed for **water caps**.

Properties

- Peelable seal to APET
- Superior mechanical strength
- Excellent stiffness
- Excellent machinability and flatness
- Good dimensional stability
- Excellent chemical resistance
- Easy open peelable seals
- The film shelf life is 6 months

Applications

It is specially designed for use in lidding applications where peelable seal property is needed to APET.

Treated side may be used as printing and lamination surface, but should be approved with present ink and glue systems used including aging tests.

Please contact customer service representative for the application compliance.

Technical Features

PROPERTIES	TEST METHOD	UNITS	BT 7011 HWX		
THICKNESS	ASTM F2251	micron	15	18	33
		Gauge	60	72	132
YIELD	ASTM D4321	m ² /kg	50,5	41,7	22,
		in ² /Lbs	35.500	29.300	15628
UNIT WEIGHT	ASTM D4321	g/m ²	19,8	24	45
GLOSS (45 °)	ASTM D2457	%	70		
OXYGEN TRANSMISSION RATE (23°C-0%RH)	ASTM D3985	cc/m ² /24hrs	≤ 100		
		cc/100in ² /24hrs	≤ 6,5		
WATER VAPOUR TRANSMISSION RATE (38°C-90%RH)	ASTM F1249	g/m ² /24hrs	≤ 30		
		g/100in ² /24hrs	≤ 2		
TENSILE STRENGTH AT BREAK	ASTM D882	MD	N/mm ²	240	
			lb/in ²	34.800	
		TD	N/mm ²	260	
			lb/in ²	37.700	
ELONGATION AT BREAK	ASTM D882	MD	140		
		TD	%		
THERMAL SHRINKAGE (150 °C, 30 min, air)	ASTM D1204	MD	%		
		TD	2,0		
COEFFICIENT OF FRICTION	ASTM D1894	Coated Side/Metal		0,50	
		Other Side/Metal		0,40	
SURFACE TENSION	ASTM D2578	Dyne/cm	Chemical Side	48	
			Other Side	-	
HEATSEAL RANGE	ASTM F88	°C		90-240	
		°F		194-464	
HEATSEAL STRENGTH to APET (150 °C, 4 MPa, 1 s)	Internal	N/15mm	3,5		

Product Identification (Decision 97/129/EC): PET1

Regulatory Status

Our product complies with the applicable EC legislation on packaging involving direct contact with foods except metallized films. Full details are given on the Regulatory Compliance Certificate and can be found on our web site.

The information contained in this data sheet is true and accurate according to current state of our knowledge and intended to give general information on our products and their applications. Above values are to be considered as guidelines and not as product specifications. Since the actual conditions of use are beyond our control, users are advised to make their own tests at their specific conditions of laboratory and/or actual use. We suggest our customers to determine final suitability for their specific end uses.

Also be advised that information on this data sheet shall not be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing, pending or future patents. The film shelf life is 6 months. Modified PU based ink series offer good adhesion and printability..

For related spec sheet with tolerance values, please contact our sales departments

STANDARD ROLL DIMENSIONS			
CORE INNER DIAMETER (ID)	CORE OUTER DIAMETER (OD)	LENGTH TOLERANCE	WIDTH TOLERANCE
76 mm (3 in) & 152 mm (6 in)	530 mm & 790 mm	± % 10 for all OD's	- 0 & + 4 mm