



# SUPEX 2011 M

## **Description**

SUPEX 2011 M is a transparent, coextruded, biaxially oriented polypropylene (BOPP) film formulated with low COF and stable slip property. Both sides heat sealable and one side treated.

General purpose packaging film for use on HFFS and VFFS packaging machines where the strong seal and low COF is required for smooth and trouble-free running.

## **Properties**

- · Excellent hot tack and heat seal strength
- · Low and stable slip
- · Excellent hot slip property
- · High clarity and gloss
- Excellent adhesion to inks and adhesives
- · Resistance to chemicals, greases and oils
- The film shelf life is 12 months





### **Technical Features**

| PROPERTIES                                   | TEST<br>METHOD | UI               | NITS            | 2011 M  |        |        |        |        |        |        |        |        |        |  |  |
|--|----------------|------------------|-----------------|---------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--|--|
| THICKNESS                                    | ASTM<br>F2251  | micron           |                 | 15      | 17     | 17,5   | 18     | 20     | 25     | 30     | 35     | 40     | 50     |  |  |
|  |                | Gauge            |                 | 60      | 68     | 70     | 72     | 80     | 100    | 120    | 140    | 160    | 200    |  |  |
| YIELD  | ASTM           | m²/kg            |                 | 73,3    | 64,6   | 62,8   | 61,1   | 54,9   | 44,0   | 36,6   | 31,4   | 27,5   | 22,0   |  |  |
|  | D4321          | in²/Lbs          |                 | 51.500  | 45.400 | 44.100 | 43.000 | 38.600 | 30.900 | 25.800 | 22.100 | 19.300 | 15.500 |  |  |
| UNIT WEIGHT                                  | ASTM<br>D4321  | g/m²             |                 | 13,7    | 15,5   | 15,9   | 16,4   | 18,2   | 22,8   | 27,3   | 31,8   | 36,4   | 45,5   |  |  |
| HAZE   | ASTM<br>D1003  | %                |                 | 1,7 2,0 |        |        |        |        |        |        |        |        |        |  |  |
| GLOSS (45°)                                  | ASTM<br>D2457  |                  | %               |         |        | 96     |        |        |        |        |        |        |        |  |  |
| TENSILE<br>STRENGTH AT<br>BREAK              | ASTM<br>D882   |                  | N/mm²           | 160     |        |        |        |        |        |        |        |        |        |  |  |
|  |                | MD               | lb/in²          | 23.200  |        |        |        |        |        |        |        |        |        |  |  |
|  |                | TD               | N/mm²           | 280     |        |        |        |        |        |        |        |        |        |  |  |
|  |                |                  | lb/in²          | 40.600  |        |        |        |        |        |        |        |        |        |  |  |
| ELONGATION                                   | ASTM           | MD               | %               | 185     |        |        |        |        |        |        |        |        |        |  |  |
| AT BREAK                                     | D882           | TD               |                 | 65      |        |        |        |        |        |        |        |        |        |  |  |
| THERMAL                                      | ASTM<br>D1204  | MD               | %               |         | 3      |        |        |        |        |        |        |        |        |  |  |
| SHRINKAGE<br>(120 °C, 5 min, air)            |                | TD               | 70              | 1       |        |        |        |        |        |        |        |        |        |  |  |
| COEFFICIENT                                  | ASTM           | Film/Film        |                 | 0,20    |        |        |        |        |        |        |        |        |        |  |  |
| OF FRICTION                                  | D1894          | Film             | n/Metal         |         |        |        | 0,20   |        |        |        |        |        |        |  |  |
| SURFACE<br>TENSION                           | ASTM<br>D2578  | Dyne/            | Treated<br>Side | 38      |        |        |        |        |        |        |        |        |        |  |  |
|  |                | cm Other<br>Side |                 |         |        |        |        |        |        |        |        |        |        |  |  |
| HEATSEAL                                     | ASTM F88       | °C               |                 | 105-145 |        |        |        |        |        |        |        |        |        |  |  |
| RANGE  |                | °F               |                 | 221-293 |        |        |        |        |        |        |        |        |        |  |  |
| HEATSEAL<br>STRENGTH<br>(120 °C, 1 MPa, 1 s) | ASTM F88       | N/15mm           |                 | 2,0     |        |        |        |        |        |        |        |        |        |  |  |

#### "Product Identification (Decision 97/129/EC): PP5"

#### Regulatory Status

Our product complies with the applicable EC legislation on packaging involving direct contact with foods except metallized films. Full details are given on the Regulatory Compliance Certificate and can be found on our web site.

The film can also be supplied with ISCC+ certified raw materials with the category of bio-circular feedstock under the product group of SUPRENEW and category of circular feedstock under the product group of SUPCYCLE. SUPRENEW and SUPCYCLE products are certified with "Mass Balance" chain of custody system under ISCC+ and due to chemical processing of the feedstock, there is no compromise & change on any specific feature of the film given in this TDS regardless of the sustainable content in the film. Therefore all product properties of this film covers the same product code with SUPRENEW or SUPCYCLE brand. Three digits will be added to the end of the ISCC+ certified product code. SUPRENEW products will be differentiated with Rxx (R will communicate that the film is circular xx code will communicate the sustainable content % of the film) and SUPCYCLE products will be differentiated with Pxx (P will communicate that the film is circular xx code will communicate the sustainable content % of the film). Further details of the sustainable content of the film will be given in the Sustainability Declaration (SD) prepared for each ISCC+ certified order.

The information contained in this data sheet is true and accurate according to current state of our knowledge and intented to give general information on our products and their applications. Above values are to be considered as guidelines and not as product specifications. Since the actual conditions of use are beyond our control, users are advised to make their own tests at their specific conditions of laboratory and/or actual use. We suggest our customers to determine final suitability for their specific end uses.

Also be advised that information on this data sheet shall not be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing, pending or future patents.

For related spec sheet with tolerance values, please contact our sales departments

| STANDARD ROLL DIMENSIONS             |                          |                        |                 |  |  |  |  |  |  |
|--------------------------------------|--------------------------|------------------------|-----------------|--|--|--|--|--|--|
| CORE INNER DIAMETER (ID)             | CORE OUTER DIAMETER (OD) | LENGTH TOLERANCE       | WIDTH TOLERANCE |  |  |  |  |  |  |
| 76 mm (3 in) & 152 mm (6 in)         | 530 mm & 790 mm *        | ± % 5 for ≤ 390 mm OD  | - 0 & + 4 mm    |  |  |  |  |  |  |
| 70 11111 (5 111) & 132 11111 (6 111) | 330 11111 & 730 11111    | ± % 10 for > 390 mm OD | -04 + 411111    |  |  |  |  |  |  |

\* 790 mm OD is available for BOPP films above 350 mm width

Factory & Head Office



REV: 03 Date: 20.03.2025