



SUPLAIN

9301 CSR

Description

SUPLAIN 9301 CSR is a one side lightly treated matt layer with release property, biaxially oriented polypropylene film. No heat seal property. One side is treated.

Matt print lamination film for high value added products. It can be laminated to paper, board, BOPP, PET and other substrates. Matt finish layer gives non-reflective surface, for better visual capability for special applications like book cover, menu, billboard, poster, etc.

Matt side is specifically designed to be used as improved release surface on cold seal structures. We strongly advise to perform trials at actual conditions and structures since very different types of cold seal systems are used.

Properties

- Matt appearance on lightly -treated side
- Improved release property on matt side against cold seal
- Excellent adhesion to inks and coatings
- Excellent adhesion to lamination adhesives
- Low static property
- Resistance to chemicals, greases and oils
- Excellent machinability
- Good moisture barrier
- Excellent dimensional stability
- The film shelf life is 6 months

Technical Features

| PROPERTIES | TEST METHOD | UNITS | | 9301 CSR |
|--|-------------|----------------------|--------------------|----------|
| THICKNESS | ASTM F2251 | micron | | 20 |
| | | Gauge | | 80 |
| YIELD | ASTM D4321 | m ² /kg | | 58,8 |
| | | in ² /Lbs | | 41.400 |
| UNIT WEIGHT | ASTM D4321 | g/m ² | | 17,0 |
| HAZE | ASTM D1003 | % | | 80 |
| GLOSS (45 °) (*) | ASTM D2457 | % | | 12 |
| TENSILE STRENGTH AT BREAK | ASTM D882 | MD | N/mm ² | 130 |
| | | | lb/in ² | 18.900 |
| | | TD | N/mm ² | 240 |
| | | | lb/in ² | 34.700 |
| ELONGATION AT BREAK | ASTM D882 | MD | % | 160 |
| | | TD | | 60 |
| THERMAL SHRINKAGE (120 °C, 5 min, air) | ASTM D1204 | MD | % | 3 |
| | | TD | | 1 |
| COEFFICIENT OF FRICTION | ASTM D1894 | Film/Film | | 0,30 |
| | | Film/Metal | | 0,20 |
| SURFACE TENSION | ASTM D2578 | Dyne/cm | Treated Side | 38 |

(*) Matt surface

“Product Identification (Decision 97/129/EC): PP5”

Regulatory Status

Our product complies with the applicable EC legislation on packaging involving direct contact with foods except metallized films. Full details are given on the Regulatory Compliance Certificate and can be found on our web site.

The film can also be supplied with ISCC+ certified raw materials with the category of bio-circular feedstock under the product group of SUPRENEW and category of circular feedstock under the product group of SUPCYCLE. SUPRENEW and SUPCYCLE products are certified with “Mass Balance” chain of custody system under ISCC+ and due to chemical processing of the feedstock, there is no compromise & change on any specific feature of the film given in this TDS regardless of the sustainable content in the film. Therefore all product properties of this film covers the same product code with SUPRENEW or SUPCYCLE brand. Three digits will be added to the end of the ISCC+ certified product code. SUPRENEW products will be differentiated with Rxx (R will communicate that the film is circular xx code will communicate the sustainable content % of the film) and SUPCYCLE products will be differentiated with Pxx (P will communicate that the film is circular xx code will communicate the sustainable content % of the film). Further details of the sustainable content of the film will be given in the Sustainability Declaration (SD) prepared for each ISCC+ certified order.

The information contained in this data sheet is true and accurate according to current state of our knowledge and intended to give general information on our products and their applications. Above values are to be considered as guidelines and not as product specifications. Since the actual conditions of use are beyond our control, users are advised to make their own tests at their specific conditions of laboratory and/or actual use. We suggest our customers to determine final suitability for their specific end uses.

Also be advised that information on this data sheet shall not be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing, pending or future patents.

For related spec sheet with tolerance values, please contact our sales departments

| STANDARD ROLL DIMENSIONS | | | |
|------------------------------|--------------------------|---|-----------------|
| CORE INNER DIAMETER (ID) | CORE OUTER DIAMETER (OD) | LENGTH TOLERANCE | WIDTH TOLERANCE |
| 76 mm (3 in) & 152 mm (6 in) | 530 mm & 790 mm * | ± % 5 for ≤ 390 mm OD ± % 10 for > 390 mm OD | - 0 & + 4 mm |

* 790 mm OD is available for BOPP films above 350 mm width

REV: 02 Date: 20.03.2025